

TABLE 1
Gradation Requirements, LS-602

MTO Sieve Designation	Percent Passing by Mass					
	Class 1 (Note 1)	Class 2	Class 3 (Note 2)	Class 4	Class 5 (Note 1)	Class 6 (Note 3)
19.0 mm	--	100	100	--	--	--
16.0 mm	--	98-100	96-100	--	--	100
13.2 mm	100	75-95	67-86	--	--	96-100
9.5 mm	75-100	50-80	29-52	100	100	50-73
6.7 mm	0-40	--	--	--	40-85	--
4.75 mm	0-10	25-50	0-10	70-100	5-25	0-10
2.36 mm	--	--	--	10-100	0-10	--
1.18 mm	--	10-40	--	5-90	0-5	--
600 µm	--	--	--	3-70	--	--
300 µm	--	2-20	--	2-40	--	--
150 µm	--	2-13	--	0-15	--	--
75 µm	Note 4	2-7	Note 4	0-7	Note 4	Note 4

Notes:

1. Class 1 and Class 5 aggregates shall be washed according to OPSS 1001.
2. Class 3 aggregate has the same gradation requirements as HL4 coarse aggregate.
3. Class 6 aggregate has the same gradation requirements as HL3 coarse aggregate.
4. Class 1, 3, 5, and 6 requirements for percent passing 75 µm are shown in Table 2.